

Portland Cement Type I/II

Description

Pakmix[®] Portland Cement Type I/II provides the basic performance characteristics of Type I Portland Cement as well as the moderate sulfate resistance and lower heat of hydration characteristic of Type II Portland Cement. Pakmix[®] Portland Cement Type I/II is an exceptionally versatile basic building material, suitable for a variety of concrete construction applications and meets ASTM C-150 in the Standard Specification for Portland Cement.

Mixing Ratio for Concrete

Part Cement	1
Parts Sand	2
Parts Gravel	3

Mixing Ratio for Mortar

Part Cement	1
Parts Lime	1/2
Parts Sand	3 1/2 to 4 1/2

47 lb bag



94 lb bag



CAUTION • AVOID CONTACT WITH SKIN • INJURIOUS TO EYES Contains Portland Cement (CAS #65997-15-1). Freshly mixed cement, mortar, concrete, grout, or stucco may cause skin injury including severe alkali burns. If exposed, wash skin promptly and repeatedly for 15 minutes and get prompt medical attention. The use of gloves and protective eye wear is recommended. If any cement or cement mixtures get into the eye, rinse immediately and repeatedly with water for 15 minutes and get prompt medical attention.

WARNING INHALATION HAZARD Avoid inhalation of dust from this product, which contains crystalline silica and other chemicals, which may cause lung disease and cancer. Use with mechanical ventilation or respiratory protection (dust mask).

EXCLUSION OF INCIDENTAL AND CONSEQUENTIAL DAMAGES Neither the manufacturer nor the retailer of this product shall be liable for any incidental or consequential damages caused by the use of this product.

KEEP OUT OF REACH OF CHILDREN

DISCLAIMER AND LIMITATION OF LIABILITY This material is warranted to be of good quality. Upon receipt of a claim within one year from the date of sale, defective material will be replaced or the purchase price refunded at the option of the manufacturer. Except for the foregoing, all warranties, express or implied, including merchantability and fitness for a particular purpose, are excluded. No liability is assumed for any consequential, incidental or special damages arising directly or indirectly from the use of the material.